



perbandingan nilai kuat tekan terhadap nilai kuat tarik belah dan kuat lentur

Variasi	Nilai Kuat Tekan (Mpa)	Nilai Kuat Tarik Belah (Mpa)	Persentase (9-15%)
Normal	45,87	4,11	8,96
Kulit Kerang 4%	46,16	4,21	9,12
Kulit Kerang 6%	36,38	4,34	11,93
Kulit Kerang 8%	40,33	4,27	10,59
Kulit Kerang 10%	45,06	4,07	9,03



Variasi	Nilai Kuat Tarik Belah (Mpa)	Nilai Kuat Lentur (Mpa)
Normal	4,11	6,36
Kulit Kerang 4%	4,21	6,71
Kulit Kerang 6%	4,34	7,29
Kulit Kerang 8%	4,27	7,29
Kulit Kerang 10%	4,07	7,33



Variasi	Nilai Kuat Tekan (Mpa)	Nilai Kuat Lentur (Mpa)	Persentase (9-15%)
Normal	45,87	6,36	13,87
Kulit Kerang 4%	46,16	6,71	14,54
Kulit Kerang 6%	36,38	7,29	20,04
Kulit Kerang 8%	40,33	7,29	18,08
Kulit Kerang 10%	45,06	7,33	16,27

